

ADVANTAGE

NON-FR STITCHBOND FILLER CLOTH

	SPECIFICATION	TOLERANCE	TEST METHOD
Material Properties			
FIBER BLEND	Polyester		
Physical Properties			
WEIGHT	2.65 osy	+/- 10%	ASTM D3776
THICKNESS	0.019 inches	+/- 10%	ASTM D5729
TENSILE STRENGTH	MD 55 pounds	+/- 10%	ASTM D5035
	CD 25 pounds	+/- 10%	ASTM D5035
TEAR STRENGTH	MD 10 pounds	+/- 10%	ASTM D2261
	CD 8 pounds	+/- 10%	ASTM D2261
ELONGATION	MD = 15%	+/- 10%	ASTM D5035
	CD = 58%	+/- 10%	ASTM D5035
DRY CROCKING		Min. 3-4	AATCC 8/116
Geometric Properties			
ROLL WIDTH	82 inches		
ROLL LENGTH	200 yards		
Packaging			
FILM CORE	3 mil poly bag 2 inch cardboard		

• HIGH-STRENGTH NON-FR STITCHBOND POLYESTER FILLER CLOTH WITH A DURABLE, NON-SKID SURFACE DESIGNED FOR DEMANDING MATTRESS FOUNDATION AND SUPPORT APPLICATIONS

• EASY-SEW CONSTRUCTION WITH NO BUILDUP ON SEWING NEEDLES, HELPING IMPROVE EFFICIENCY AND REDUCE WASTE DURING MANUFACTURING

• AVAILABLE IN 82" WIDE ROLLS OR CUT-TO-SIZE PANELS FOR EFFICIENT HANDLING ON THE PRODUCTION FLOOR

