HEXCEL

RIPSTOP PERFORMANCE NYLON

MATERIAL PROPERTIES: Nylon 6.6, Polyurethane Coating

	SPECIFICATION	TOLERANCE	TEST METHOD
Weight	3.5 osy Nylon, 1 osy PU	+/- 10%	ASTM D3776
Tensile Strength	MD = 211 pounds	+/- 10%	ASTM D5035
	CD = 180 pounds	+/- 10%	ASTM D5035
Tear Strength	MD = 40 pounds	+/- 10%	ASTM D5587
	CD = 54 pounds	+/- 10%	ASTM D5587

Roll width: 92" | Roll length: 200yds | Roll diameter: 9" | Film: 3 mil Poly Bag | Core: 2" Cardboard

- **HIGH-STRENGTH 210 DENIER NYLON WITH POLYURETHANE COATING AND HEXAGON RIPSTOP AESTHETIC ENGINEERED FOR ENHANCED TEAR STRENGTH IN HEALTHCARE, DORMITORY, AND INSTITUTIONAL MATTRESS APPLICATIONS**

- **FLUID-PROOF, ANTIMICROBIAL SURFACE HELPING PROTECT AGAINST STAINS, MOISTURE, MOLD, MILDEW, AND EVERYDAY WEAR**

- **AVAILABLE WITH INTEGRATED FR BARRIER LAMINATION AND SLIT-TO-WIDTH ROLL OPTIONS FOR CUT-AND-SEW OPTIMIZATION**

CARE INSTRUCTIONS: Clean with mild soap and water only. Disinfection is unnecessary due to inherent antimicrobial properties.

NFPA 701 FLAME RESISTANT

COMPLIANT PROPOSITION 65

QUALITY AWARD 2015 WINNER ★ Johnson Controls ★ EXCELLENCE IN EXECUTION

COMPLIANT CFR 1633