

PURL FT®

	SPECIFICATION	TOLERANCE	TEST METHOD
Material Properties			
Fiber Blend	Naturally Crimped Wool Inherent FR Rayon Bicomponent Polyester	+/- 5% +/- 5% +/- 5%	ASTM D629-99 ASTM D629-99 ASTM D629-99
Physical Properties			
Weight Range Thickness	0.5 - 1.0 osf 0.5 inches	+/- 10% +/- 10%	ASTM D3776 ASTM D5729
Thermal Properties			
Peak Temperature Char Elongation Char Force	475-625°F 0.4 1.2	Maximum	PCC LP-100-1
Aesthetics			
Color Odor	White None		

Roll width: 90" | Roll length: 60-100yds | Roll weight: 93lbs | Film: 4 mil Double Poly Bag | Core: 2" Cardboard

- ✦ **PROVEN HI-LOFT FR BARRIER ENHANCED WITH NEW ZEALAND WOOL INTEGRITY— CERTIFIED WOOL FOR IMPROVED RESILIENCE AND PERFORMANCE ACROSS A WIDE RANGE OF MATTRESS CONSTRUCTIONS**
- ✦ **INHERENT FR BARRIER COMBINED WITH WOOL’S NATURAL FLAME-RESISTANT PROPERTIES, DELIVERING RELIABLE CFR 1633 PROTECTION WITH NO ADDED CHEMICAL TREATMENTS**
- ✦ **WOOL COMPONENT SUPPORTS MOISTURE REGULATION, CONTRIBUTING TO IMPROVED BREATHABILITY AND COMFORT WITHIN THE SLEEP SYSTEM**

